

# MicroTopp PU 300W semi gloss



## TYPE OF PRODUCT

Two-component waterborne semi gloss transparent top-coat based on polyurethane resin.

## APPLICATION AREA

- Transparent seal coat on MicroTopp flooring system

## PROPERTIES

- Semi gloss surface appearance;
- Increased resistance to standard chemicals that can affect floor surface
- increased wear and scratch resistance
- very low odor
- easy maintenance of the floor

## TECHNICAL DATA

- Mixing ratio (by mass): Component A: Component B – 91,7 : 8,3
- Solid content: By weight: ~ 32,87 %
- Pot life: 6 h under standard conditions
- Drying/hardening time under standard conditions:
  - dust dry: after approx. 45 minutes
  - foot traffic: after approx. 24 hours
  - fully hardened: 3 days

## MATERIAL PREPARATION

Stir the component A. Then add component B into component A and mix thoroughly, manually or with a mixer with a low speed (max. 400 r / min) until a homogeneous mixture. Leave the mixture to stay for the 15 minutes. Then pour the mixture into another container and mix again. The mixture should be used within 6 hours.

## APPLICATION METHOD

Uniformly spread MicroTopp PU 300W by using a short pile microfiber roller. Apply the material crosswise and uniformly in a thin layer. Connected surfaces should be worked "wet on wet" to avoid visible over-lapping areas.

Last update: January 2025

Limitation of Liability. The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Chromos, whether in technical documentation or in response to specific enquiry or otherwise are based on data which to the best of our knowledge are reliable. It is end users responsibility to determine the suitability of the product for its intended use. Producer has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Chromos does therefore not accept any liability arising from loss, injury or damage resulting from such use. The data contained herein are liable to modification as result of practical experience and continuous product development.



### APPLICATION OF MICROTOPP SYSTEM

1. Apply one or two layers of MicroTopp BC with a metal steel trowel, depending on the type of substrate. On floor always apply two layers. Before application of the second layer, sand the first layer with abrasive paper 100/120 and remove dust. Apply the second layer 8-12 hours after applying the first layer.
2. Continue further surface preparation with the MicroTopp FC decorative cement. Apply one layer of MicroTopp FC with a metal steel trowel 12 hours after applying MicroTopp BC. Before application of the MicroTopp FC sand the layer of the MicroTopp BC with abrasive paper 120/150 and remove dust.
3. Continue with the work at least 12 hours after applying MicroTopp FC decorative cement. Sand the MicroTopp FC with abrasive paper 150/180 and remove dust. As a primer, use diluted PU 300W (with 5% of water). After 4 hours, apply the second coat of water-based transparent top coat PU 300W. Apply the final layer of transparent PU 400W coating 12-24 hours after applying the second layer of PU 300W coating.

### APPLICATION CONDITIONS

Substrate and air temperature: min. +10 °C; max. +30 °C  
 Relative air humidity: max. 75 %, with adequate ventilation.  
 There must be no condensation. Pay attention to the dew point.

### CLEANING

Clean all tools and application equipment with water immediately after use. Hardened and/or cured material can only be removed mechanically.

### SPREADING RATE

0,20 kg/m<sup>2</sup> – primer.  
 0,08 - 0,12 kg/m<sup>2</sup> per layer – top coat.

### PACKAGING

	Component A	Component B	Primer	Top coat
5 kg (A+B)	4,59 kg	0,41 kg	Enough for: cca 25 m <sup>2</sup>	Enough for: cca 20 m <sup>2</sup>
15 kg (A+B)	13,76 kg	1,24 kg	cca 75 m <sup>2</sup>	cca 60 m <sup>2</sup>

Last update: January 2025

Limitation of Liability. The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Chromos, whether in technical documentation or in response to specific enquiry or otherwise are based on data which to the best of our knowledge are reliable. It is end users responsibility to determine the suitability of the product for its intended use. Producer has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Chromos does therefore not accept any liability arising from loss, injury or damage resulting from such use. The data contained herein are liable to modification as result of practical experience and continuous product development.



#### STORAGE

In dry and good ventilated space at temperatures from +5°C to+30°C.  
Shelf life: 12 months. Keep from freezing and direct sun light.

#### COLOUR RANGE/GLOSS

Transparent, semi-glossy.

#### DISPOSAL

Empty packaging completely and dispose of in accordance with regulations. For the disposal of product residues, waste water and containers with adherent product residues please follow the local governmental regulations.

#### SAFETY PRECAUTIONS

See relevant material safety data sheet and label.

Last update: January 2025

Limitation of Liability. The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Chromos, whether in technical documentation or in response to specific enquiry or otherwise are based on data which to the best of our knowledge are reliable. It is end users responsibility to determine the suitability of the product for its intended use. Producer has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Chromos does therefore not accept any liability arising from loss, injury or damage resulting from such use. The data contained herein are liable to modification as result of practical experience and continuous product development.

**Chromos boje i lakovi d.d.**  
Radnička cesta 173d  
10000 Zagreb, Hrvatska

Phone: +385 1 2410 666  
Fax: +385 1 2405 512  
[www.chromos.eu](http://www.chromos.eu)

