

CHROMODEN AQUA 2K PARQUET LACQUER REPAIR

Chromoden®



TYPE OF PRODUCT

Two-component waterborne colourless lacquer

APPLICATION AREA

For quick renew of old parquet lacquered with Chromoden parquet lacquers (Chromoden aqua and Chromoden solventborne) in spaces medium to strong load (offices, halls, corridors, pharmacies, kindergartens ...)

FEATURES

- for renovation and refresh of old lacquered parquet
- suitable for renovation of parquet with Chromoden waterborne and Chromoden solventborne lacquer and finished parquet without removing old layers of lacquer
- quick renew
- durability and abrasion resistance
- high hardness
- easy to clean and resistant to splash of mild chemicals

PROPERTIES

Density: cca 1025kg/m³ (HRN EN ISO 2811-1)
Solids content (w.%): 30-35 (HRN EN ISO 3251)

DILUTION

No dilution. If necessary add CHROMODEN AQUA retardants to 5 % (in terms of high temperatures, low relative humidity and larger surface)

EU VOC VALUES AND LIMITS

A (j), 140 g/l (2010); This product contains: maks 140 g/l

SURFACE REQUIREMENTS

Surface (floor) should be dry, free of oil, dirt and possibly old paints and sanded (final sanding paper No. 150 or No. 120 for a single-plate polishing machine and No. 80-100 if Trio sander is used). After sanding, remove all dust with a vacuum cleaner. Surface must not be bleached with hydrogen peroxide or other chemicals.

Last update: September 2020

Limitation of Liability. The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Chromos, whether in technical documentation or in response to specific enquiry or otherwise are based on data which to the best of our knowledge are reliable. It is end users responsibility to determine the suitability of the product for its intended use. Producer has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Chromos does therefore not accept any liability arising from loss, injury or damage resulting from such use. The data contained herein are liable to modification as result of practical experience and continuous product development.

Chromoden®



INSTRUCTION FOR USE

Before use it is necessary to stir each component separately.

Lacquer and contact mix in a clean dry plastic container in vol. ratio 10: 1

(CHROMODEN AQUA 2K REPAIR COMP. A: CHROMODEN AQUA HARDENER FOR 2K PARQUET LACQUER COMP B)

The mixture should be thoroughly homogenized and before applying on the parquet let stand for About 15 minutes and stir again.

If necessary, filter before applying on the parquet. The mixture is usable for 4 hours.

APPLICATION

Lacquer is applied by special roller in one or two layers of the viscosity of delivery.

The interlayer interval is 4-8 hours. Dried first layer of lacquer slightly be sanded No. 240 to 320. Dust should be removed with a vacuum cleaner. Space can be used 24 to 48 hours after applying the final coat.

DRYING

Depending on the conditions it dries 4- 8 h.

SPREADING RATE

ca. 10-12 m²/l in one layer (cca 0,08-0,1 l/m²)

PACKAGING

CHROMODEN AQUA 2K PU LACQUER RAPIR COMP A: plastic containers á 5 l

CHROMODEN AQUA HARDENER FOR 2K PARQUET LACQUER COMP B: plastic containers á 0,5 l

STORAGE

At least until the deadline printed on the label, in factory sealed packaging, in dry and ventilated place at a temperature of +5 ° C to +25 ° C

SHELF LIFE

18 months.

The product should not be frozen!

NOTE

Parquet humidity should be between 8 and 10 %. The optimum operating conditions are 18-22 °C, relative humidity 40-75 % and temperature of parquet should not be lower than 12 °C. Moisture in the floor must be from 8 to 10 %. The room temperature as well as the temperature of the aqua lacquers and paints

Last update: September 2020

Limitation of Liability. The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Chromos, whether in technical documentation or in response to specific enquiry or otherwise are based on data which to the best of our knowledge are reliable. It is end users responsibility to determine the suitability of the product for its intended use. Producer has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Chromos does therefore not accept any liability arising from loss, injury or damage resulting from such use. The data contained herein are liable to modification as result of practical experience and continuous product development.

Chromoden®



must not be lower than 13 °C.

The room is used after 48 hours, and the tool is washed with water immediately after use.

Before application on exotic wood surfaces please contact our experts from field service department.

After use, close tightly plastic containers.

Last update: September 2020

Limitation of Liability. The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Chromos, whether in technical documentation or in response to specific enquiry or otherwise are based on data which to the best of our knowledge are reliable. It is end users responsibility to determine the suitability of the product for its intended use. Producer has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Chromos does therefore not accept any liability arising from loss, injury or damage resulting from such use. The data contained herein are liable to modification as result of practical experience and continuous product development.

Chromos boje i lakovi d.d.
Radnička cesta 173d
10000 Zagreb, Hrvatska

Phone: +385 1 2410 666
Fax: +385 1 2405 512
www.chromos.eu

 **Chromos**