

CHROMOLUX PRIMER

Chromolux®



TYPE OF PRODUCT

Primer based on combination of oil-modified, air-drying polyurethane and alkyd resin in organic solvents, with the addition of pigment and fillers.

APPLICATION AREA

Pigmented white primer for the protection of the different wood surfaces (doors, windows, wooden constructions, ...)

VISCOSITY

2 100 - 2 900 mPa s (HRN EN ISO 3219:2002)

MASS DENSITY

1 210 - 1 250 kg/m³ (HRN EN ISO 2811-1:2004)

THINNING

No thinning.

SURFACE REQUIREMENTS

The substrate must be clean, dry, sanded with sandpaper no. 150 to no. 180, free of dirt and dust. Before applying CHROMOLUX PRIMER we recommended for outer surfaces also one layer of fungicide-insecticidal impregnation. Unevenness should be leveled with CHROMOLUX PUTTY FOR WOOD. For outside surfaces we recommend putty only for small areas, while the inner surface can be leveled whole.

INSTRUCTIONS FOR USE

Stir well before use. Apply with a brush or by spraying (air or airless) in 1-2 layers. The dried layer sand with sandpaper no. 220 to no. 240. After application the tools should be cleaned by LUXAL SINTETIC THINNER.

DRYING

Each layer under normal conditions ($t = 20^\circ\text{C}$, 65% rel. humidity) dried 24 hours. By lower temperatures and higher relative humidity, drying time is prolonged.

Last update: July 2014

Limitation of Liability. The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Chromos, whether in technical documentation or in response to specific enquiry or otherwise are based on data which to the best of our knowledge are reliable. It is end users responsibility to determine the suitability of the product for its intended use. Producer has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Chromos does therefore not accept any liability arising from loss, injury or damage resulting from such use. The data contained herein are liable to modification as result of practical experience and continuous product development.



Chromolux®

SPREADING RATE

0,08 - 0,10 l/m² (10 – 12,5 m²/l) in one layer

EU VOC CATEGORY AND LIMITS

IIA(g), 350 g/l (2010); product contains: max. 350 g/l

PACKAGING

0,75; 2,5 l.

STORAGE

In dry and good ventilated space at temperatures from +5 °C to +25 °C.

Shelf life: 5 years.

SAFETY

The information about the safe handling, storage and disposal of products please check in the Safety Data Sheet.

Last update: July 2014

Limitation of Liability. The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Chromos, whether in technical documentation or in response to specific enquiry or otherwise are based on data which to the best of our knowledge are reliable. It is end users responsibility to determine the suitability of the product for its intended use. Producer has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Chromos does therefore not accept any liability arising from loss, injury or damage resulting from such use. The data contained herein are liable to modification as result of practical experience and continuous product development.