

# FASADEX SN BOND

**Fasadex**<sup>®</sup>



## PRODUCT DESCRIPTION

Impregnation concentrate based on acrylic copolymer dispersion.

## APPLICATION AREA

Deep primer for increasing the adhesion of the new coatings on old substrates. Reduces and equalizes the absorptivity of the porous mineral surfaces and thus prepare it for application of plasters and dispersion paints.

## PROPERTIES

- deeply penetrates into the substrate
- reduces and equalizes the absorptivity of the substrate
- binds surface loose particles
- improves the adhesion and provides a solid bond of the new coatings on old substrate.

## DENSITY

900-1100 kg/m<sup>3</sup>

## APPLICATION TEMPERATURE

From +5 °C to +35 °C

## THINNING

With pure water at a ratio 1: 5 (one part of impregnation and five parts of water).

## EU VOC CATEGORY AND LIMITS

IIA (h), 30 g / l (2010); the product contains max. 0,1 g / l

## SUBSTRATE QUALITY/ PREPARATION

The surface must be dry, clean, firm, without oil stains and dust.

## APPLICATION

By brush, fur roller or spraying in one or two coats, depending on the surface absorption.

## DRYING

4- 5 hours under normal conditions. After drying the surface is ready for further processing stages.

Last update: April 2021.

Limitation of Liability. The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Chromos, whether in technical documentation or in response to specific enquiry or otherwise are based on data which to the best of our knowledge are reliable. It is end users responsibility to determine the suitability of the product for its intended use. Producer has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Chromos does therefore not accept any liability arising from loss, injury or damage resulting from such use. The data contained herein are liable to modification as result of practical experience and continuous product development.

**Fasadex<sup>®</sup>**



#### CONSUMPTION

0.20 to 0.25 l / m<sup>2</sup> (4-5 m<sup>2</sup> / l) of diluted impregnation in one layer, depending on the roughness and absorptivity of the substrate.

#### PACKAGING

Plastic packaging, 1 and 5 l

#### STORAGE

In dry and ventilated place at a temperature of + 5 °C to 25 °C.

Durability: 24 months.

Last update: April 2021.

Limitation of Liability. The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Chromos, whether in technical documentation or in response to specific enquiry or otherwise are based on data which to the best of our knowledge are reliable. It is end users responsibility to determine the suitability of the product for its intended use. Producer has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Chromos does therefore not accept any liability arising from loss, injury or damage resulting from such use. The data contained herein are liable to modification as result of practical experience and continuous product development.

**Chromos boje i lakovi d.d.**  
Radnička cesta 173d  
10000 Zagreb, Hrvatska

Phone: +385 1 2410 666  
Fax: +385 1 2405 512  
[www.chromos.eu](http://www.chromos.eu)

